


DENSOLEN[®] System 2

DENSOLEN[®]-N12/-090/-R20 HT

Product information



Special advantages:



For operating temperatures up to +50°C (+122°F).



Fulfills EN 12068-C 50.



Highly resistant thanks to three-tape design.



Proven over many years in countless pipeline projects.

Robust field coating system for the corrosion prevention of pipelines and pipeline components.

For a century now, DENSO Group Germany has been representing experience, quality and reliability for corrosion prevention and sealing technology. The success of the internationally leading corporation is based on the development of the "DENSO-Tape", which was already patented in 1927 as the first product worldwide for the passive corrosion prevention of pipelines. Since then, the DENSO Group Germany has been establishing and guaranteeing the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees continuously implement safe and individual solutions in a personal cooperation with the customer.

Description

DENSOLEN[®] System 2 is a robust field coating system for the permanent corrosion prevention of pipelines and pipeline components. DENSOLEN[®] System 2 is a highly stressable system based on its design of three **DENSOLEN[®]** tapes, which has proven itself outstandingly in many construction measures on transportation and distribution pipelines.

DENSOLEN[®] System 2 features an ÖVGW approval for the stress class C 50 in accordance with EN 12068. The requirements for this standard are exceeded.

Standard designation:

- EN 12068 - C 50



DENSOLEN[®] System 2 consists of three **DENSOLEN[®]** tapes that have been proven for a long time:

DENSOLEN[®]-N12 as the inner tape, assumes the major corrosion prevention properties of the system. The thick butyl rubber layer of the tape equalizes unevenly formed surfaces and permits an easy processing on pipelines with small as well as large nominal pipe sizes. Due to its self-amalgamation effect in the overlapping area, DENSOLEN[®]-N12 creates an essentially gas and water tight as well as electrically high insulating encasement.

DENSOLEN[®]-090 is used as the middle layer in the encasement system. It is a flexible two-ply tape with a polyethylene outside layer and a butyl rubber coating positioned on the inside. The applied winding tension presses the inside tape solidly to the component surface and thus supports the self-amalgamation of the inside tape.

DENSOLEN[®]-R20 HT is a robust two-ply tape. The solid polyethylene outside layer protects the coating against mechanical stresses.

All three **DENSOLEN[®]** tapes can be processed efficiently with the **DENSOMAT[®]** wrapping devices.

Typical product properties

Property	Unit	DENSOLEN®-N12 Typical value	DENSOLEN®-090 Typical value	DENSOLEN®-R20 HT Typical value	Test method
Carrier film color	-	-	yellow	white, black or blue	-
Butyl adhesive color inside	-	grey	grey	black	-
Butyl adhesive color outside	-	grey	-	-	-
Tape thickness	mm	≥1.2	≥0.4	≥0.5	ISO 4591 ASTM D1000
Carrier film thickness app.	mm	≥0.07	≥0.26	≥0.3	
Inside adhesive layer thickness app.	mm	≥0.7	≥0.14	≥0.2	
Outside adhesive layer thickness app.	mm	≥0.43	-	-	
Elongation at break	%	≥500	≥400	≥500	DIN 30672
Tape strength	+23°C (+73°F) N / cm	≥30	≥35	≥65	EN 12068
Dielectric strength	kV / mm	-	-	≥50	ASTM D149

Property	Unit	DENSOLEN® System 2 Typical value	Required value	Test method
System design	Primer	DENSOLEN®-HT Primer	-	-
	Inner tape	DENSOLEN®-N12, 2 layers		
	Tensioning tape	DENSOLEN®-090, 2 layers		
	Outer tape	DENSOLEN®-R20 HT, 2 layers		
Total thickness	mm	≥4.2	-	-
Specific electrical insulation resistance	Ohm m ²	≥10 ¹⁰	≥10 ⁸	EN 12068
Peel strength to steel	+23°C (+73°F)	≥15	≥10	EN 12068
	+50°C (+122°F)	≥5	≥1	
Peel strength layer to layer	N12 / N12	≥30	≥15	EN 12068
	N12 / 090	≥25	≥15	
	090 / 090	≥2	≥2	
	R20 HT / R20 HT	≥3	≥2	
Indentation resistance (residual layer thickness)	+23°C (+73°F) (10 MPa) mm	≥0.6	≥0.6	EN 12068
Impact resistance	J	>20	≥15	EN 12068
Cathodic disbondment (radius)	mm	<9	<20	EN 12068
Lap shear strength	on steel N/cm ²	15	≥5	EN 12068

DENSOLEN® tapes can be easily applied manually. The processing with the original DENSO MAT® wrapping devices is even more efficient. For DENSOLEN® tapes with widths of > 50 mm, we recommend the use of the DENSO MAT® wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

	Core diameter (mm)	Width (mm)	Tape length (m)	Tape area (m ²)	Content per box			App. Weight (kg)
					Number of rolls	Total tape area (m ²)	Total tape length (m)	
DENSOLEN®-N12	41	50	10	0.5	12	6.0	120	10
		75		0.75	12	9.0	120	15
		100		1.0	6	6.0	60	10
DENSOLEN®-090	41	50	15	0.75	12	9.0	180	6.5
		75		1.125	12	13.5	180	10.0
		100		1.5	6	9.0	90	6.5
DENSOLEN®-R20 HT	41	30	15	0.45	18	8.1	270	5.0
		50		0.75	12	9.0	180	5.5
		75		1.125	12	13.5	180	8.0
		100		1.5	6	9.0	90	5.5
		50	30	1.5	12	18	360	11.0
		75		2.25	12	27	360	17.0
		100		3.0	6	18	180	11.0
		150		4.5	6	27	180	17.0

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, DENSOLEN®-N12/-090/-R20 HT can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.

DENSO GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@denso-group.com
www.denso-group.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks of DENSO, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.denso-group.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, which is available at www.denso-group.com, shall be decisive. The legal relationship shall be governed by German law.

06.2022